

Premium Tile Adhesive (C2)

Guide Formulation

Mineral base mixture	Parts by Weight
Portland cement	35-45
Limestone flour < 0,1 mm	5-10
Quartz or Limestone sand 0,1 - 0,4 mm	40-55

Additives	Parts by Weight
KimaCell Cellulose ether	0.35-0.55
Redispersible Polymer powder	2-4

Optimizing additives	Parts by Weight
Cellulose fibres < 0,4 mm	0,1 -0,3
High aluminate cement	1 -3
Calcium formate	0,4-0,8